

中国认可
国际互认
检测
TESTING
CNAS L0422

南京海关工业产品检测中心

Nanjing Customs District Industrial Products Inspection Center

检验检测报告
TESTING REPORT

编号No.: 320003-SC24-RC1998

日期Date: 2024年07月11日

客户信息:			
委托单位:	江苏苏美达伊顿纪德品牌管理有限公司		
委托单位地址:	南京市玄武区长江路190号6F		
样品信息:			
样品名称:	运动T恤 藏青松绿白		
纤维成分:	100% 聚酯纤维		
样品数量:	3件	商标品牌:	—
规格型号:	—	产品等级:	合格品
订单号:	—	其他:	—
生产单位:	—		
生产单位地址:	—		
款号:	CLTHNEW00000		
(以上信息由委托人确认并提供)			
实验室对样品的说明:			
实验室样品描述:	T恤		
收样日期:	2024-07-08	检测日期:	2024-07-08 ~ 2024-07-11
检测类别:	委托检测	样品状态:	符合检验要求
到样数量:	3件	安全类别:	B类
检测项目及方法:	按委托单位要求选择	检验检测结论:	符合
检测判定依据:	GB 31701-2015《婴幼儿及儿童纺织产品安全技术规范》、GB/T 22854-2009《针织学生服》		
首页备注:	—		

批准:

审核:

编制:

1、委托检验仅对收到的样品负责,不承担其他连带责任。This report is valid only for the samples delivered by clients. 2、对报告若有异议,应于收到报告之日起15日内向本中心提出,逾期不再受理。If there is any objection concerning the report, it is required that the objection should be put forth to the center within 15 days from the reception date of the report. 3、除非客户要求,本报告检测结果及符合性判定不考虑测量结果的不确定度。Measurement uncertainty is not considered on the results and conformity assessment in the report unless required by the customer. 4、除全文复制外,未经本中心书面批准,不得部分复制报告。Except for full text reproduction, partial reproduction of the report is not allowed without written approval from our center.

地址(Address): 南京市创智路39号39# Chuangzhi Rd. Nanjing, CHINA 电话(Tel): 86-25-52345198 / 86-25-52345170 / 86-25-52345545

E-mail: fzs_gyp_gov@163.com

JSIC-FZB001-C3



230020348365

中国认可
国际互认
检测
TESTING
CNAS L0422

第 2 页 / 共 6 页



南京海关工业产品检测中心

Nanjing Customs District Industrial Products Inspection Center

检验检测报告
TESTING REPORT

编号No.: 320003-SC24-RC1998

日期Date: 2024年07月11日

检测结果:

序号	检验项目	检测方法	检测结果	要求值	单项判定	
1	异味	GB 18401-2010	无	无	合格	
2	甲醛含量(mg/kg)	GB/T 2912.1-2009	未检出	≤75	合格	
3	pH值	GB/T 7573-2009 0.1mol/L KCl溶液	6.0	4.0~8.5	合格	
4	可分解致癌芳香胺染料(mg/kg)	GB/T 17592-2011	4-氨基联苯	未检出	≤20	合格
			联苯胺	未检出	≤20	合格
			4-氯邻甲苯胺	未检出	≤20	合格
			2-萘胺	未检出	≤20	合格
			邻氨基偶氮甲苯	未检出	≤20	合格
			5-硝基-邻甲苯胺	未检出	≤20	合格
			对氯苯胺	未检出	≤20	合格
			2,4-二氨基苯甲醚	未检出	≤20	合格
			4,4'-二氨基二苯甲烷	未检出	≤20	合格
			3,3'-二氯联苯胺	未检出	≤20	合格
			3,3'-二甲氧基联苯胺	未检出	≤20	合格
			3,3'-二甲基联苯胺	未检出	≤20	合格
			3,3'-二甲基-4,4'-二氨基二苯甲烷	未检出	≤20	合格
			2-甲氧基-5-甲基苯胺	未检出	≤20	合格
			4,4'-亚甲基-二-(2-氯苯胺)	未检出	≤20	合格
4,4'-二氨基二苯醚	未检出	≤20	合格			
4,4'-二氨基二苯硫醚	未检出	≤20	合格			
邻甲苯胺	未检出	≤20	合格			

1、委托检验仅对收到的样品负责，不承担其他连带责任。This report is valid only for the samples delivered by clients. 2、对报告若有异议，应于收到报告之日起15日内向本中心提出，逾期不再受理。If there is any objection concerning the report, it is required that the objection should be put forth to the center within 15 days from the reception date of the report. 3、除非客户要求，本报告检测结果及符合性判定不考虑测量结果的不确定度。Measurement uncertainty is not considered on the results and conformity assessment in the report unless required by the customer. 4、除全文复制外，未经本中心书面批准，不得部分复制报告。Except for full text reproduction, partial reproduction of the report is not allowed without written approval from our center.

地址(Address): 南京市创智路39号39# Chuangzhi Rd. Nanjing, CHINA 电话(Tel): 86-25-52345198 / 86-25-52345170 / 86-25-52345545

E-mail: fzs_gyp_gov@163.com

JSIC-FZB001-C3



230020348365

中国认可
国际互认
检测
TESTING
CNAS L0422

第 3 页 / 共 6 页



南京海关工业产品检测中心

Nanjing Customs District Industrial Products Inspection Center

检验检测报告
TESTING REPORT

编号No.: 320003-SC24-RC1998

日期Date: 2024年07月11日

检测结果:

序号	检验项目		检测方法	检测结果	要求值	单项判定
4	可分解致癌芳香胺染料 (mg/kg)	2,4-二氨基甲苯	GB/T 17592-2011	未检出	≤20	合格
		2,4,5-三甲基苯胺		未检出	≤20	合格
		邻氨基苯甲醚		未检出	≤20	合格
		4-氨基偶氮苯		未检出	≤20	合格
		2,4-二甲基苯胺		未检出	≤20	合格
		2,6-二甲基苯胺		未检出	≤20	合格
5	燃烧性能		GB/T 14644-2014	NA*	—	—
6	附件锐利性	锐利边缘(个)	GB/T 31702-2015	无附件	无	合格
		锐利尖端(个)		无附件	无	合格
7	绳带要求(7岁以上)	头、颈部	GB 31701-2015	符合	头部和颈部调整服装尺寸的绳带不应有自由端,其他绳带不应有长度超过75mm的自由端。头部和颈部:当服装平摊至最大尺寸时不应有突出的绳圈,当服装平摊至合适的穿着尺寸时突出的绳圈周长不应超过150mm;除肩带和颈带外,其他绳带不应使用弹性绳带。	合格
		背部		符合	除腰带外,背部不应有绳带伸出或系着。	合格

1、委托检验仅对收到的样品负责,不承担其他连带责任。This report is valid only for the samples delivered by clients. 2、对报告若有异议,应于收到报告之日起15日内向本中心提出,逾期不再受理。If there is any objection concerning the report, it is required that the objection should be put forth to the center within 15 days from the reception date of the report. 3、除非客户要求,本报告检测结果及符合性判定不考虑测量结果的不确定度。Measurement uncertainty is not considered on the results and conformity assessment in the report unless required by the customer. 4、除全文复制外,未经本中心书面批准,不得部分复制报告。Except for full text reproduction, partial reproduction of the report is not allowed without written approval from our center.

地址(Address): 南京市创智路39号39# Chuangzhi Rd. Nanjing, CHINA 电话(Tel): 86-25-52345198 / 86-25-52345170 / 86-25-52345545

E-mail: fzs_gyp_gov@163.com

JSIC-FZB001-C3



中国认可
国际互认
检测
TESTING
CNAS L0422



南京海关工业产品检测中心

Nanjing Customs District Industrial Products Inspection Center

检验检测报告 TESTING REPORT

编号No.: 320003-SC24-RC1998

日期Date: 2024年07月11日

检测结果:

序号	检验项目		检测方法	检测结果	要求值	单项判定
8	残留金属针		GB 31701-2015	符合	婴幼儿及儿童纺织产品的包装中不应使用金属针等锐利物。婴幼儿及儿童纺织产品上不允许残留金属针等锐利物。	合格
9	顶破强力(N)		GB/T 19976-2005 钢球的直径为38mm±0.02mm	1294	≥180	合格
10	水洗尺寸变化率(%)	直向	GB/T 8878-2014;GB/T 8629-2001 5A/悬挂晾干	-0.2	-6.5~+3.0	合格
		横向		-0.8	-6.5~+3.0	合格
11	水洗后扭曲率(%)		GB/T 22854-2009 5A/悬挂晾干	0.6	≤7.0	合格
12	耐皂洗色牢度(级)	原样变色	GB/T 3921-2008 A(1)	4-5	≥3	合格
		涤沾色		4-5	≥3	合格
		棉沾色		4-5	≥3	合格
13	耐酸汗渍色牢度(级)	原样变色	GB/T 3922-2013	4-5	≥3	合格
		涤沾色		4-5	≥3	合格
		棉沾色		4-5	≥3	合格
14	耐碱汗渍色牢度(级)	原样变色	GB/T 3922-2013	4-5	≥3	合格
		涤沾色		4-5	≥3	合格
		棉沾色		4-5	≥3	合格
15	耐水色牢度(级)	原样变色	GB/T 5713-2013	4-5	≥3	合格
		涤沾色		4-5	≥3	合格
		棉沾色		4-5	≥3	合格
16	耐干摩擦色牢度(级)	直向	GB/T 3920-2008	4-5	≥3	合格

1、委托检验仅对收到的样品负责,不承担其他连带责任。This report is valid only for the samples delivered by clients. 2、对报告若有异议,应于收到报告之日起15日内向本中心提出,逾期不再受理。If there is any objection concerning the report, it is required that the objection should be put forth to the center within 15 days from the reception date of the report. 3、除非客户要求,本报告检测结果及符合性判定不考虑测量结果的不确定度。Measurement uncertainty is not considered on the results and conformity assessment in the report unless required by the customer. 4、除全文复制外,未经本中心书面批准,不得部分复制报告。Except for full text reproduction, partial reproduction of the report is not allowed without written approval from our center.

地址(Address): 南京市创智路39号39# Chuangzhi Rd. Nanjing, CHINA 电话(Tel): 86-25-52345198 / 86-25-52345170 / 86-25-52345545

E-mail: fzs_gyp_gov@163.com

JSIC-FZB001-C3



230020348365

中国认可
国际互认
检测
TESTING
CNAS L0422

第 5 页 / 共 6 页



南京海关工业产品检测中心

Nanjing Customs District Industrial Products Inspection Center

检验检测报告
TESTING REPORT

编号No.: 320003-SC24-RC1998

日期Date: 2024年07月11日

检测结果:

序号	检验项目		检测方法	检测结果	要求值	单项判定
17	耐湿摩擦色牢度(级)	直向	GB/T 3920-2008	4-5	$\geq 2-3$	合格
18	耐光色牢度(级)		GB/T 8427-2019 方法3	好于3	≥ 3	合格
19	耐光、汗复合色牢度(碱性)(级)		GB/T 14576-2009	4	$\geq 2-3$	合格
20	起球(级)		GB/T 4802.1-2008 压力780cN, 起毛次数0次, 起球次数600次	4.5	≥ 3.0	合格
21	纤维含量(%)		FZ/T 01057.3~4-2007 GB/T 2910.11-2009	藏青色部位/绿色部位: 100聚酯纤维	100聚酯纤维	合格
22	拼接互染程度(级)	沾色	GB/T 22854-2009 附录B	4-5	$\geq 3-4$	合格
23	外观	表面疵点	GB/T 22854-2009	符合	符合标准表2规定。	合格
		色差(级)		4-5	主料之间 ≥ 4 级, 主辅料之间 $\geq 3-4$ 级	合格
		本身尺寸差异		符合	符合标准表4规定。	合格
		缝制规定		符合	符合标准4.4.5规定。	合格
备注	<p>“未检出”指检测结果小于检出限, 甲醛(分光光度法)检出限为20mg/kg, 可分解致癌芳香胺染料检出限为5mg/kg;</p> <p>“—”表示无相关要求值, 不作判定;</p> <p>*NA表示外层面料单位面积质量$>90\text{g}/\text{m}^2$ ($194\text{g}/\text{m}^2$), 不考核燃烧性能。</p>					



1、委托检验仅对收到的样品负责, 不承担其他连带责任。This report is valid only for the samples delivered by clients. 2、对报告若有异议, 应于收到报告之日起15日内向本中心提出, 逾期不再受理。If there is any objection concerning the report, it is required that the objection should be put forth to the center within 15 days from the reception date of the report. 3、除非客户要求, 本报告检测结果及符合性判定不考虑测量结果的不确定度。Measurement uncertainty is not considered on the results and conformity assessment in the report unless required by the customer. 4、除全文复制外, 未经本中心书面批准, 不得部分复制报告。Except for full text reproduction, partial reproduction of the report is not allowed without written approval from our center.

地址(Address): 南京市创智路39号39# Chuangzhi Rd. Nanjing, CHINA 电话(Tel): 86-25-52345198 / 86-25-52345170 / 86-25-52345545

E-mail: fzs_gyp_gov@163.com

JSIC-FZB001-C3



南京海关工业产品检测中心

Nanjing Customs District Industrial Products Inspection Center

检验检测报告 编号No.: 320003-SC24-RC1998
TESTING REPORT 日期Date: 2024年07月11日

样品照片/贴样:



照片/贴样仅限于随本报告使用

** **

1、委托检验仅对收到的样品负责，不承担其他连带责任。This report is valid only for the samples delivered by clients. 2、对报告若有异议，应于收到报告之日起15日内向本中心提出，逾期不再受理。If there is any objection concerning the report, it is required that the objection should be put forth to the center within 15 days from the reception date of the report. 3、除非客户要求，本报告检测结果及符合性判定不考虑测量结果的不确定度。Measurement uncertainty is not considered on the results and conformity assessment in the report unless required by the customer. 4、除全文复制外，未经本中心书面批准，不得部分复制报告。Except for full text reproduction, partial reproduction of the report is not allowed without written approval from our center.

地址(Address): 南京市创智路39号 39# Chuangzhi Rd. Nanjing, CHINA 电话(Tel): 86-25-52345198 / 86-25-52345170 / 86-25-52345545
E-mail: fzs_gyp_gov@163.com

JSIC-FZB001-C3